

wherein component B of the coating mixture is a water-soluble polyepoxy compound;

wherein component C of the coating mixture comprises particles with an average

particle diameter between 0.001 and 1.0 μm ;

wherein the coating mixture is present in an amount between 0.005 and 0.030 g/m^2 ,
based on dry weight;

wherein the polyamide film is either unstretched or is uniaxially stretched and non-heated before being coated with the coating mixture; and

wherein after being coated with the coating mixture, the polyamide film is stretched in at least one direction and heated.

29. (Amended) The polyamide film as described in claim 8, wherein the non-ionic surface active agent is contained at a content of 0.01 - 1.0%, based on the solid content of the aqueous dispersion of polyurethane.

REMARKS

Claims 8-14 are pending herein. This Amendment amends claim 8 and 9 to better conform the claim language to the specification. The attached appendix includes a marked-up copy of the amended claims (37 CFR §1.121(c)(ii)). No new matter is added.

It is respectfully submitted that the instant application is in condition for allowance. A prompt and favorable examination on the merits is respectfully solicited.

RECEIVED
JUL 19 2001
TC 1700 MAIL ROOM

24